



Norcros SA: TAL goldflex grout

- ❖ [Go to Specifile](#)
- ❖ [Click here to view supplier details](#)
- ❖ [See full brochure](#)

TAL GOLDFLEX GROUT®



DESCRIPTION

TAL GOLDFLEX GROUT is a single part rapid setting ceramic tile grout, specifically formulated using dry form polymers to incorporate flexibility, water resistance, increased strength and non-slump properties. These characteristics, normally only achieved by the use expensive admixtures, can now be achieved by simply adding water, reducing the risk of mixing errors. The grout is fully set in just 3 hours. (When used in conjunction with TAL RAPID SET ADHESIVES the tiled area can be subjected to full traffic 6 hours after fixing.)

FEATURES

- Built in flexibility
- Water and frost resistant
- High strength
- No additives required
- Just add water
- Suitable for wall and floor joints
- Suitable for joints between 3 - 20 mm wide
- Interior and exterior

AREAS OF APPLICATION

TAL GOLDFLEX GROUT is suitable for use in interior and exterior, light or heavy-duty installations as well as areas subjected to semi or permanent moisture or permanent water immersion such as showers or swimming pools. It is also suitable for substrates prone to deflection or vibration. Its excellent durability makes it suitable for use in areas such as hotels, shopping centres, restaurants, car showrooms, hospitals and factories. It is also suitable for use in residential bathrooms, kitchens and hallways.

TAL GOLDFLEX GROUT can be specified for all types of wall and floor ceramic tile installations with grout joints between 3 and 20 mm wide. It is also suitable for grouting joints between mosaics, quarry and terrazzo tiles, brick pavers and natural stone. It is **not** recommended for use with soft glazed wall tiles.

DIRECTIONS

The adhesive should be completely dry and joints clean before grouting. Add 20 kg of TAL GOLDFLEX GROUT to 3.5 litres of clean water. Mix well until a thick uniform consistency is achieved. No further water should be added to the mix. The working time of the mixture is approximately 45 minutes at 20°C

Working in small areas, apply the grout to the joints at a 45° angle using a TAL GROUT SQUEEGEE. Ensure the joints are fully compacted with grout. Excess grout should be removed from the face of the tiles. Allow about 15 minutes for the grout to dry before cleaning off with a damp TAL SPONGE. Polish the tiles with a clean, dry cloth when the grout is sufficiently set.

The grout can be subjected to normal service conditions after 3 hours. (Ensure the adhesive used is sufficiently set before grouting and subjecting to traffic.)



TAL GOLDFLEX GROUT®



DESCRIPTION

TAL GOLDFLEX GROUT is a single part rapid setting ceramic tile grout, specifically formulated using dry form polymers to incorporate flexibility, water resistance, increased strength and non-s slump properties. These characteristics, normally only achieved by the use expensive admixtures, can now be achieved by simply adding water, reducing the risk of mixing errors. The grout is fully set in just 3 hours. (When used in conjunction with TAL RAPID SET ADHESIVES the tiled area can be subjected to full traffic 6 hours after fixing.)

FEATURES

- Built in flexibility
- Water and frost resistant
- High strength
- No additives required
- Just add water
- Suitable for wall and floor joints
- Suitable for joints between 3 - 20 mm wide
- Interior and exterior

AREAS OF APPLICATION

TAL GOLDFLEX GROUT is suitable for use in interior and exterior, light or heavy-duty installations as well as areas subjected to semi or permanent moisture or permanent water immersion such as showers or swimming pools. It is also suitable for substrates prone to deflection or vibration. Its excellent durability makes it suitable for use in areas such as hotels, shopping centres, restaurants, car showrooms, hospitals and factories. It is also suitable for use in residential bathrooms, kitchens and hallways.

TAL GOLDFLEX GROUT can be specified for all types of wall and floor ceramic tile installations with grout joints between 3 and 20 mm wide. It is also suitable for grouting joints between mosaics, quarry and terrazzo tiles, brick pavers and natural stone. It is **not** recommended for use with soft glazed wall tiles.

DIRECTIONS

The adhesive should be completely dry and joints clean before grouting. Add 20 kg of TAL GOLDFLEX GROUT to 3.5 litres of clean water. Mix well until a thick uniform consistency is achieved. No further water should be added to the mix. The working time of the mixture is approximately 45 minutes at 20°C

Working in small areas, apply the grout to the joints at a 45° angle using a TAL GROUT SQUEEGEE. Ensure the joints are fully compacted with grout. Excess grout should be removed from the face of the tiles. Allow about 15 minutes for the grout to dry before cleaning off with a damp TAL SPONGE. Polish the tiles with a clean, dry cloth when the grout is sufficiently set.

The grout can be subjected to normal service conditions after 3 hours. (Ensure the adhesive used is sufficiently set before grouting and subjecting to traffic.)



Technical Advice Centre Toll-free Number: 0800 008 008



Add 20kg Goldflex Grout to 3.5l clean cool water.



Mix well while adding powder.



Working time of the mixture is 45 min.



Apply grout.



Clean off excess grout.

Solutions Through Technology

Another successful installation guaranteed

A **NORCROS** COMPANY



TAL GOLDFLEX GROUT®

COVERAGES

Coverage will vary according to tile size and joint width. The following are approximate coverages :

TILE SIZE	JOINT WIDTH	APPROXIMATE COVERAGE
150 x 150 x 6mm	3mm	0.50kg/m ²
250 x 200 x 9mm	3mm	0.50kg/m ²
250 x 200 x 9mm	6mm	1.00kg/m ²
240 x 115 x 12mm	8mm	2.50kg/m ²
300 x 300 x 9mm	6mm	0.75kg/m ²

STORAGE AND SHELF LIFE

When stored under cover between 5°C and 30°C, the product has a shelf life of 6 months. Never store directly on a concrete floor.

PACKAGING

Available in 20kg bags.

WARNING

DO NOT INGEST • USE ONLY AS DIRECTED • WEAR PROTECTIVE GLOVES AND GOGGLES • USE A SUITABLE DUST MASK
• WORK IN WELL VENTILATED AREAS.

TAL GUARANTEE

TAL products are manufactured to the highest standards and are guaranteed to be free from manufacturing defects and fit for design purpose. TAL products must be used strictly in accordance with TAL's methods and materials specifications and good working practice.

TAL TECHNICAL ADVISORY SERVICE

For a detailed methods and materials specification contact the TAL TECHNICAL ADVICE CENTRE on our toll free line on 0800 008 008 or fax (011) 316 3127.

PRECAUTIONS

To avoid staining of tiles, apply grout to a small trial area of tiles before proceeding. When grouting external installations, provide adequate protection against inclement weather conditions during grouting and for as long as possible after completion of the grouting.

Do not use TAL GOLDFLEX GROUT in temperatures below 5°C.

Swimming pools should not be filled for at least 72 hours after grouting has been completed.

In areas where chemicals are aggressive or where chemical balances are difficult to maintain TAL EPOXY GROUT is recommended.

CONTACT DETAILS

Toll free Technical helpline 0800 008 008

Johannesburg: (011) 316 3133 • Cape Town (021) 386 1810 • Durban (031) 700 1535

TAL reserves the right to change the information on this datasheet.

Another successful installation guaranteed

